

## Technical Data Sheet

Ferrofluid Type: PBG 200

### Specifications and Physical Properties

	CGS Units	SI Units
<b>Appearance</b>		Black-brown fluid
<b>Carrier Liquid</b>		Water-miscible
<b>Saturation Magnetization</b>	220 Gauss	22 mT
<b>Viscosity @ 27°C</b>	<2 cP	<2 mPa·s
<b>Avg. Particle Size</b>		10 nm
<b>Density</b>	1.19 g/ml	1.19 g/cm <sup>3</sup>
<b>Volume % Particle Concentration</b>		3.9
<b>pH</b>		7 - 8
<b>Nature of Surfactant</b>		Nonionic

*Note: There is a tendency for magnetic particles to form aggregates in water based ferrofluids. PEG coated ferrofluids are far more stable than standard water-based fluids, however observed behavior will be subject to actual storage conditions.*

Please contact your local office for information on the tolerances of these values.

**For further technical data, please contact your local Ferrotec office:**

Ferrotec (USA) Corporation, USA  
Ferrotec Corporation, Japan  
Ferrotec (Iberia) S.A., Spain  
Ferrotec Shanghai, China  
Ferrotec Singapore, Singapore

(603) 472-6800  
+81-479-73-6752  
+34 9 16 13 16 53  
+86-21-63542967  
+65-293-1011

[info@ferrotec.com](mailto:info@ferrotec.com)  
[ffsales@ferrotec.co.jp](mailto:ffsales@ferrotec.co.jp)  
[mvazquez@ferrotec.com](mailto:mvazquez@ferrotec.com)  
[baowg@ferrotec.com.cn](mailto:baowg@ferrotec.com.cn)  
[info@ferrotec.com.sg](mailto:info@ferrotec.com.sg)